

	Technical Data Sheet	ClickGuard™
Kronoflooring GmbH Lampertswalde Mühlbacher Straße 1 01561 Lampertswalde	Clickguard™	Last modified: 15.01.2013

Clickguard™

Product information:

Clickguard™ is a colourless, non resinous one – component adhesive based on natural rubber. It is easy processable. The dried adhesive can be combined with natural latex. Clickguard™ is used for example for hand folding and so stick lining materials or insoles.

Typical properties:

Solids content:	11% approx.
Adjusted viscosity:	high – viscosity
Density at 20 °C (g/ cm³):	0.7 approx.
Flash point:	< 21 °C
Appearance:	colourless, transparent
Film resistance:	water insoluble

Instructions for use:

Method of application:	brush, roller coater
Coating weight:	250 g/ m² approx. wet, depends on substrate
Pot life (100 g mixture):	8 hours approx (addition of 5 phr)
Bonding:	contact or one – way application (wet)
Drying:	at room temperature
Drying before fitting:	10 minutes approx., depends on substrate
Wet bonding:	until 12 hours, depends on substrate

Shelf life and storage conditions:

Storage conditions:	at 5 to 25 °C an excess of the recommended storage temperature during transport is not critical
Shelf life:	12 months in sealed original containers
Low temperature stability:	frost resistant; thickens on cooling, ready for use after warming to room temperature

Hazard data:

**see MSDS conforms to regulation (EC)
No. 1907/ 2006 (REACH) Annex II Germany**

Legal notes

The information, and, in particular, the recommendations relating to the application and end – use of Kronoflooring products, are given in good faith based on Kronoflooring's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Kronoflooring's recommendations. In practice, the differences in materials, substances and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Kronoflooring reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.